

Produced by:	Phoenix Compounding Technology GmbH		
Sold by:	Continental Reifen Deutschland GmbH/ Retread Business		
Production date:	30.12.2024		
ArticleNumber:	17080500000		
Specification:	100151739	C01777 FM	0421 570
Lot Numbers:	04954	-----	04998

Test parameters	Standards	Unit	Target value	Lower Limit Upper Limit	Laboratory values
Hardness Shore A	DIN 53505	Shore A	53	48-58	54,00
Specific density	DIN EN 1183-1	g/cm ³	1,09	1,07-1,11	1,08
Viscosity ML 1+3 / 100°C	DIN 53523	MU	30,0	25,0-35,0	31,54
Rheometer t10 / 150°	DIN 53529	Min	1,5	0,90-2,10	1,14
Rheometer t90 / 150°	DIN 53529	Min	4,7	3,5-5,5	4,46
Tear strength	DIN 53504	N/mm ²	17,0	13,0 ---	22,44
Elongation at break	DIN 53504	%	550	470 ---	590,20
Module 300%	DIN 53504	N/mm ²	7,3	4,3-10,3	8,40
Elasticity	DIN 53512	%	54,0	49,0-59,0	57,12

This certificate is valid without signature. Our test certificates are based on the characteristics of the product immediately after production. However, the certificate does not absolve the customer from re-confirming or inspection of the material received in accordance with the requirements for the correct quality for the individual processes. The properties of the product are influenced by the transport conditions and storage. This product is intended for industrial processing or use only. The average values are statistically valid and apply to the entire order.